

# 無膠雙面板

## Adhesiveless Double Side FCCL

### I. 主要特性 Features

1. 極佳的撓曲性及剝離強度 Outstanding flexibility and peel strength;
2. 優異的耐熱性和耐化學品性 Excellent thermal resistance and chemical resistance;
3. 良好的尺寸穩定性 Good dimensional stability;
4. 無鹵無銻符合 ROHS 要求 Halogen free and antimony free, meets ROHS requirements

### II. 主要性能表 General Properties

Item	Type Material		IF-2LD 4M12	IF-2LD 4M18	IF-2LD 4M35	Remark					
Spec.	TPI Film (μm)		100	100	100	Width 250mm, 500mm Length 100m					
	Copper Foil (μm)		12	18	35	Standard					
Properties	Test Item		Condition	Value	Value	Value	1/3 OZ	1/2 OZ	1OZ	Test Method	
	Peel Strength (Kgf/cm)	A		90°	> 1.0	> 1.2	> 1.4	≧ 0.8	≧ 1.0	≧ 1.4	IPC-TM-650 2.4.9
		Chemical Resistance (%)	IPA	Dipping /10min	<3	<3	<3	≧ 20			IPC-TM-650 2.3.2
			NaOH		<3	<3	<3				
	HCl		<3		<3	<3					
	Water Absorption (%)		D-24/23	<2.0	<2.0	<2.0	≧ 2.0			IPC-TM-650 2.6.2	
	Solder Resistance		288°C/10S /3次	OK	OK	OK	288°C/10S/3次			IPC-TM-650 2.4.13	
	Dimensional Stability (%)	MD	Method B	-0.07~+0.03	-0.03~+0.05	-0.05~+0.05	≧ ±0.08			IPC-TM-650 2.2.4	
		TD		-0.04~+0.04	-0.04~+0.04	-0.06~+0.04					
		MD	Method C	-0.09~+0.01	-0.09~+0.01	-0.09~+0.01	≧ ±0.10				
		TD		-0.08~+0.02	-0.08~+0.02	-0.08~+0.02					
	Volume Resistance (Ω-cm)		C-96/23/65	> 2×10 <sup>13</sup>	> 2×10 <sup>13</sup>	> 2×10 <sup>13</sup>	≧ 10 <sup>13</sup>			IPC-TM-650 2.5.17	
	Surface Resistance (Ω)			> 2×10 <sup>12</sup>	> 2×10 <sup>12</sup>	> 2×10 <sup>12</sup>	≧ 10 <sup>12</sup>				
	Insulation Resistance (Ω)			> 1×10 <sup>9</sup>	> 1×10 <sup>9</sup>	> 1×10 <sup>9</sup>	≧ 10 <sup>9</sup>				IPC-TM-650 2.6.3.2
Tg(°C)		DMA	296	296	296	-			ITEQ method		
Dielectric Constant(2GHz)		C-24/23/50	3.56	3.56	3.56	≧ 4.0			IPC-TM-650 2.5.5.3		
Dissipation Factor (2GHz)			0.0067	0.0067	0.0067	≧ 0.04					

接上表

Item	Type Material		IF-2LD 5035	IF-2LD 5018	IF-2LD 7535	IF-2LD 7518	Remark					
Spec.	TPI Film ( $\mu\text{m}$ )		50	50	75	75	Width 250mm, 500mm Length 100m					
	Copper Foil ( $\mu\text{m}$ )		35	18	35	18	Standard					
Properties	Test Item		Condition	Value	Value	Value	Value	1/3 OZ	1/2 OZ	1OZ	Test Method	
	Peel Strength (Kgf/cm)	A		90°	> 1.4	> 1.2	> 1.4	> 1.2	$\geq 0.8$	$\geq 1.0$	$\geq 1.4$	IPC-TM-650 2.4.9
		Chemical Resistance (%)	IPA	Dipping /10min	<3	<3	<3	<3	$\leq 20$			IPC-TM-650 2.3.2
			NaOH		<3	<3	<3	<3				
			HCl		<3	<3	<3	<3				
	Water Absorption (%)		D-24/23	<2.0	<2.0	<2.0	<2.0	$\leq 2.0$			IPC-TM-650 2.6.2	
	Solder Resistance		288°C /10S/3 次	OK	OK	OK	OK	288°C/10S/3 次			IPC-TM-650 2.4.13	
	Dimensional Stability (%)	MD	Method B	-0.04~0.02	-0.04~0.02	-0.01~0.07	-0.01~0.05	$\leq \pm 0.08$			IPC-TM-650 2.2.4	
		TD		0.01~0.07	-0.01~0.05	-0.03~0.05	-0.01~0.05					
		MD	Method C	-0.07~-0.01	-0.08~0.02	-0.06~0.02	-0.06~0	$\leq \pm 0.10$				
		TD		-0.03~0.03	-0.05~0.01	-0.05~0.03	-0.07~0.01					
	Volume Resistance ( $\Omega \cdot \text{cm}$ )		C-96/23/65	$> 2 \times 10^{13}$	$> 2 \times 10^{13}$	$> 2 \times 10^{13}$	$> 2 \times 10^{13}$	$\geq 10^{13}$			IPC-TM-650 2.5.17	
	Surface Resistance ( $\Omega$ )			$> 2 \times 10^{12}$	$> 2 \times 10^{12}$	$> 2 \times 10^{12}$	$> 2 \times 10^{12}$	$\geq 10^{12}$				
Insulation Resistance ( $\Omega$ )		$> 1 \times 10^9$		$> 1 \times 10^9$	$> 1 \times 10^9$	$> 1 \times 10^9$	$\geq 10^9$			IPC-TM-650 2.6.3.2		
Tg(°C)		DMA	296	296	296	296	-			ITEQ method		
Dielectric Constant(2GHz)		C-24/23/50	3.55	3.55	3.56	3.56	$\leq 4.0$			IPC-TM-650 2.5.5.3		
Dissipation Factor (2GHz)			0.0068	0.0068	0.0067	0.0067	$\leq 0.04$					

### III. 儲存條件 Storage

真空包裝：30°C 以下，濕度 70% 以下，儲存一年。Vacuum Packaging: Lower than 30°C and 70%RH for one year.