



IT-8338G

CCL : IT-8338G
Prepreg: IT-8338GBS

High Tg / Low Dk / Ultra Low Loss / Halogen Free RF Microwave Product

- ANSI Type : No ANSI
- Applicable IPC-4101 / None ; IPC-4103 /240/540
- 5G Base Stations and mm Wave Applications, Power Amplifiers, Antenna Applications
- Automotive Radar, LNB's for Direct Broadcast Satellites

Laminate properties

Items	IPC TM-650	Typical Value	Unit
Peel Strength A. Low profile copper foil (35 μm)	2.4.8	4.0	lb/inch
Volume Resistivity	2.5.17.1	10 ¹⁰	MΩ-cm
Surface Resistivity	2.5.17.1	10 ¹⁰	MΩ
Moisture Absorption	2.6.2.1	0.14	%
Permittivity (Dk) A. 2 GHz B. 5 GHz C. 10 GHz	TM-mode, CDR C-24/23/50	3.38 3.38 3.38	--
Loss Tangent (Df) A. 2 GHz B. 5 GHz C. 10 GHz	TM-mode, CDR C-24/23/50	0.0023 0.0023 0.0023	--
Flexural Strength(30 mil) A. Length direction B. Cross direction	2.4.4	400-430 380-410	N/mm ²
Thermal Stress 10 sec at 288°C A. Unetched B. Etched	2.4.13.1	Pass Visual Pass Visual	Rating
Flammability	UL94	V-0	Rating
Comparative Tracking Index (CTI)	ASTM D3638/ UL 746	CTI 1 (400-599)	Class (Volts)
Maximum Operating Temperature(MOT)	UL 746	130	°C
Glass Transition Temperature(TMA)	2.4.24	185	°C
Decomposition Temperature (5% W.L)	2.4.24.6	430	°C
X/Y Axis CTE (-40°C to 150°C)	2.4.41	20	ppm/°C
Z-Axis CTE A. Alpha 1 B. Alpha 2 C. 50 to 260 Degrees C	2.4.24	60 350 3.4	ppm/°C ppm/°C %
Thermal Resistance A. T288 B. T300	2.4.24.1	> 60 > 60	Minutes Minutes